

FIG. 1
EMISSION SPECTRA OF NAFION THIN FILM CONTAINING
DIIC(5) BEFORE AND AFTER EXPOSURE TO DMMP VAPOR




FIG. 2

SENSITIVITY AND PROPORTIONALITY OF NAFION/DIIC(5) PROBE TO DMMP




FIG. 3

RESPONSE OF NILE BLUE DOPED POLYETHYLENE MALEATE FILM TO DMMP




FIG. 4

RESPONSE OF NILE RED DOPED
POLYETHYLENE MALEATE FILM TO DMMP




FIG. 5
CHANGE OF FLUDRESCENCE OF DIIC(5) IN NAFION UPON EXPOSURE TO SARIN AT 0.0099mg/m3




FIG. 6
CHANGE OF FLUDRESCENCE INTENSITY WHEN
THE FILM WAS EXPOSED TO SARIN




FIG. 7 RESPONSE OF AN OXAZINE 170/FLUOROPOLYOL FILM TO GD AT 520 ppb




FIG. 8 RESPONSE OF AN OXAZINE 170/FLUOROPOLYOL FILM TO GO AT 41 ppb




FIG. 9A RESPONSE OF NILE BLUE/PECH FILM TO HD AT 350 ppb ON 27 FEB 97




FIG. 9B NULL RESPONSE OF NILE BLUE/PECH FILM OF FIGHER 50 UPON EXPOSURE TO GO AT 166 PPB




FIG. 9C RESPONSE OF SAME NILE BLUE/PECH FILM, AFTER EXPOSURE TO GO (AT 166 ppb) UPON RE-EXPOSURE TO HD (AT 243 ppb)

FIG. 10

(SCHEME I) SYNTHESIS OF NEAR-INFRARED EXCITED SOLVATOCHROMIC FLOUROPHORE

THE CHO

CHO

CHO

1. DMF = 150°C FOR 12 HOURS
2. (C₂H₅)₃N IN E+DH

CH₃

FIG. 11

(SCHEME II) SYNTHESIS OF ARYL
NEAR-INFRARED EXCITED
SOLVTOCHROMIC FLUOROPHORE

X = S, NH, ETC.